


ENERGIZER AC675E

Zinc Air




Industry Standard Dimensions



Typical Discharge Characteristics

Schedule: 16 hours/day Typical Drain @ 1.3V: 2.1 & 1.3 milliamperes Load: 625 & 1,000 ohms



Simulated Application Test

Typical Performance at 21°C & 50% RH

Schedule:	Typical Drains: at 1.3V (milliamperes)	Load (ohms)	Cutoff 0.9V (hours)
16 Hours/Day	2.1	625	302
16 Hours/Day	1.3	1,000	488

Specifications

Chemical System: Zinc Air (Zn/O2) **Tab Color:** Blue

Designation: IEC-PR44 **Nominal Voltage:** 1.4 Volts

Typical Capacity: 635 mAh (to 0.9 volts)

(Rated at 326 ohms at 21°C/50% RH)


Typical Weight: 1.9 grams


Typical Volume: 0.5 cubic centimeters

Impedance

The total opposition that a battery offers to the flow of alternating current. Impedance is a combination of resistance and reactance.

The typical impedance of these cells on open circuit and during useful discharge varies from 5-20 ohms. This applies over a frequency range of 40-5,000 hertz at the current drains shown below.





Important Notice

This datasheet contains typical information specific to products manufactured at the time of its publication.

©Energizer Holdings, Inc. - Contents herein do not constitute a warranty.

Form No. AC675EGL1217 Page 1 of 1